

# DATA SHEET

產品品名: 輕雪銅合成紙 (2PBCTAA)  
PRODUCT: LIGHT MATTE PAPER (2PBCTAA)

項目 (ITEM)	單位 (UNIT)	結果 (RESULT)			試驗方法 (METHOD)	
		0.085mm	0.10mm	0.12mm		
厚度 (Thickness)	%	±7	±7	±7	micro-gauge	
拉力強度 Tensile Strength	MD	psi	4000 ↑	4000 ↑	4000 ↑	ASTM-D638
	CD		2500 ↑	2500 ↑		
伸長率 Elongation	MD	%	500 ↑	500 ↑	500 ↑	ASTM-D638
	CD		80 ↑	80 ↑		
撕裂強度 Tear Strength	MD	gm/mm	400 ↑	400 ↑	400 ↑	ASTM-D1922
	CD		500 ↑	500 ↑		
表面張力 Surface Tension	A	dyne/cm	46 ↑	46 ↑	46 ↑	ASTM-D2578
	B		46 ↑	46 ↑		
粗度值 (463 紋) Roughness	A	μ <sup>''</sup>	10~30	10~30	10~30	JIS-B0601
	B		25~60	25~60		
粗度值 (408 紋) Roughness	A	μ <sup>''</sup>	40~60	40~60	40~60	JIS-B0601
	B		25~60	25~60		
光澤度 Gloss Value (60°)	A	%	2~5	2~5	2~5	ASTM-D523
	B		2~5	2~5		
穿透度 Transmittance	%		18↓	18 ↓	14 ↓	ASTM-D1003
白度 Whiteness	%		84 ↑			ASTM-E313
參考比重 Specific Gravity	--		1.22 ± 0.03			ASTM-D792
表面阻抗 Surface Resistance	Ω		9 x 10 <sup>12</sup> ↓			ASTM-D257

註: 以上資料源自本公司例行之品質檢查, 僅供參考不能用於免除買方對交運成品檢查之責任, 亦不能做為其他特殊用途產品適用性之保證。

**REMARK:**

THE ABOVE INFORMATION IS DERIVED FROM OUR QUALITY CHECKS FOR REFERENCE ONLY.  
IN NEITHER RELIEVES THE PURCHASER FROM RESPONSIBILITY FOR EXAMINING THE PRODUCT  
UPON DELIVERY NOR PROVIDES ASSURANCE OF THE PRODUCT'S SUITABILITY FOR A PARTICULAR PURPOSE.