

EVERFILM®



THE FOOD WRAP FILM



EVERSPAN PTY LTD

PHYSICAL PROPERTIES

ITEM		UNIT	TESTING METHOD	HOUSEHOLD USE	FOOD STUFF USE		
					INFLATION	T-DIE	
TENSILE STRENGTH	MD	Kg/cm ²	ASTM	300	300	320	
	CD		D882	240	250	230	
ELONGATION	MD	%	ASTM	120	120	270	
	CD		D882	160	160	360	
HAZE		%	ASTM D10003	1.5 DOWNWARD			
O ₂ TRANSMISSION		ml/m ² .	ASTM	610			
CO ₂ TRANSMISSION		24hrs	D1434	650			
MOISTURE TRANSMISSION		ml/m ² . 24hrs	ASTM E96	200			
TEST OF HYGIENE	TEST OF SOLUBILITY	VAPORIZATION REMAINS OF	N-HEPTAND	PPM	150 DOWNWARD		
			ETHANOLY	PPM	30 DOWNWARD		
			ACETIC ACID	PPM	30 DOWNWARD		
			HEAVY METAL CONTENT (4% ACETIC ACID)		PPM	1 DOWNWARD	
			KMnO4 CONSUMPTION		PPM	10 DOWNWARD	
REMARKS		ABOVE IS LABORATORY TESTING RESULTS, FOR REFERENCE ONLY.					

SPECIFICATIONS

APPLICATIONS	THICKNESS (μ , micron)	WIDTH (cm)	LENGTH (M)	PACKAGING
HOUSEHOLD / CATERING	--	33,45	600 (Max.)	4RLS / CTN
COMMERCIAL USE	12 ~ 19	25 ~ 60	1300 (Max.)	2RLS / CTN

EVERSPAN PTY LTD

50 QUINN STREET PRESTON VICTORIA 3072 AUSTRALIA

TEL: (61) 3 9480 3311 FAX: (61) 3 9480 5011

<http://www.everspan.net.au>

E-MAIL: info@everspan.net.au